

# HIGH PERFORMANCE PIGMENTS



● H I L I N T E K





























NINGBO HILINTEK CO.,LTD.

High Performance Pigments		Product Name Color Index Number	Fastness Properties						Application Ranges		
			Heat (°C) Resistance	Light Fastness	Water Resistance	Oil Resistance	Acid Resistance	Alkali Resistance	Inks	Coating	Plastic
Full Color		PR122	250	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR123	250	6/7	5	5	5	5	●	●	
Tint Color											
Full Color		PR144	300	7/8	5	5	5	5			●
Tint Color											
Full Color		PR149	340	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR166	300	7	5	5	5	5			●
Tint Color											
Full Color		PR168	300	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR176	240	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR177	250	8	5	5	5	5		●	○
Tint Color											
Full Color		PR179	200	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR184	180	7	5	5	5	5	●		
Tint Color											
Full Color		PR185	250	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR188	200	7	5	5	5	5	●	●	●
Tint Color											
Full Color		PR208	200	6/7	5	4/5	4/5	4/5	●	●	●
Tint Color											
Full Color		PR242	300	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PR254	250   300	8	5	5	5	5	●	●	●
Tint Color											

● Main using ○ Suggest using

High Performance Pigments		Product Name Color Index Number	Fastness Properties						Application Ranges		
			Heat (°C) Resistance	Light Fastness	Water Resistance	Oil Resistance	Acid Resistance	Alkali Resistance	Inks	Coating	Plastic
Full Color		PR264	250	7	5	5	5	5	●	●	●
Tint Color											
Full Color		PR266	180	7	5	4/5	5	5	○	●	
Tint Color											
Full Color		PY110	250	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PY138	300	6/7	5	5	5	5	●	●	●
Tint Color											
Full Color		PY139	280	7/8	5	5	4	4	●	●	●
Tint Color											
Full Color		PY147	300	7/8	5	5	5	3			●
Tint Color											
Full Color		PY150	250	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PY151	200	8	5	5	5	5	●	●	○
Tint Color											
Full Color		PY154	160	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PY155	180	8	4/5	4/5	5	5	●	●	●
Tint Color											
Full Color		PY180	290	6/7	5	5	5	5	●	●	●
Tint Color											

● Main using ○ Suggest using

High Performance Pigments		Product Name Color Index Number	Fastness Properties						Application Ranges		
			Heat (°C) Resistance	Light Fastness	Water Resistance	Oil Resistance	Acid Resistance	Alkali Resistance	Inks	Coating	Plastic
Full Color		PY181	280	7	5	4/5	4/5	4/5	●	●	●
Tint Color											
Full Color		PY192	300	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PY194	250	7/8	5	5	5	5	●	●	○
Tint Color											
Full Color		PO36	160	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PO62	250	7/8	5	5	5	5		●	●
Tint Color											
Full Color		PO64	250	7	5	5	5	5		●	●
Tint Color											
Full Color		PO73	300	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PB25	290	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PV19	300	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PV23	250	7/8	5	5	5	5	●	●	●
Tint Color											
Full Color		PV29	300	8	5	5	5	5	○	●	●
Tint Color											
Full Color		PB15:6	300	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PB60	300	8	5	5	5	5	●	●	●
Tint Color											
Full Color		PG36	300	8	5	5	5	5	●	●	●
Tint Color											

*"Coloring the world, one pigment at a time."*



Address; Room 2802, Building 8, Financial Silicon Valley, Yinzhou District,  
Ningbo city Zhejiang province, China. 315000

Email: [info@hilintek.com](mailto:info@hilintek.com)  
Tel: 0086-19555157407  
Website: [www.hilintek.com](http://www.hilintek.com)

● Main using ○ Suggest using