

CYCOLOY™ FR RESINS C2800

REGION AMERICAS

DESCRIPTION

CYCOLOY C2800 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is a standard grade that can be injection molded. This non-chlorinated, non-brominated flame retardant PC/ABS has a UL V0 & 5VB flame rating. CYCOLOY C2800 resin is an excellent candidate for a wide variety of applications including business equipment, monitors, and enclosures.

TYPICAL PROPERTY VALUES

Revision 20191022

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D638
Tensile Modulus, 50 mm/min	2680	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	96	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	2680	MPa	ASTM D790
Hardness, Rockwell R	120	-	ASTM D785
IMPACT			
Izod Impact, notched, 23°C	427	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	58	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	90	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	73	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	80	°C	ASTM D648
CTE, -40°C to 60°C, flow	7.2E-05	1/°C	ASTM E831
CTE, -40°C to 60°C, xflow	7.2E-05	1/°C	ASTM E831
Thermal Conductivity	0.2	W/m-°C	ASTM C177
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	70	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.17	-	ASTM D792
Specific Gravity, color	1.18	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.1	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.4	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	16	g/10 min	ASTM D1238
ELECTRICAL			
Volume Resistivity	1.E+17	Ω.cm	ASTM D257
Surface Resistivity	>1.E+14	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	17.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3	-	ASTM D150

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Permittivity, 100 Hz	3	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0048	-	ASTM D150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-221031	-	-
UL Recognized, 94V-2 Flame Class Rating	0.88	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	1.47	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2.31	mm	UL 94
Oxygen Index (LOI)	35	%	ASTM D2863
INJECTION MOLDING			
Drying Temperature	75 – 80	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	230 – 275	°C	
Nozzle Temperature	230 – 275	°C	
Front - Zone 3 Temperature	225 – 275	°C	
Middle - Zone 2 Temperature	215 – 260	°C	
Rear - Zone 1 Temperature	210 – 255	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.